

① Stratobel Clearlite 88.2 Annealed

Performance data

☀️ Light properties - EN 410

Light transmission : τ_v [%]	86
External light reflection : ρ_v [%]	8
Internal light reflection : ρ_{vi} [%]	8
Colour rendering index : R_a [%]	98

🔥 Energy properties - EN 410

Solar factor : g [%]	75
External energy reflection : ρ_e [%]	6
Internal energy reflection : ρ_{ei} [%]	7
Direct energy transmission : τ_e [%]	69
Energy absorption glass 1 : α_{e1} [%]	25
Total energy absorption : α_e [%]	25
Shading coefficient : SC	0.86
UV transmission : τ_{uv} [%]	0
Selectivity	1.15

🌡️ Thermal properties - EN 673

Thermal transmittance (vertical) : U_g [W/(m ² .K)]	5.3
Thermal transmittance (Roof, horizontal) : U_g [W/(m ² .K)]	5.3

☀️ Summer solar factor - RT 2012

Sg1 : Sg1 [%]	69
Sg2 : Sg2 [%]	9
Sg3 : Sg3 [%]	0

☀️ Winter solar factor - RT 2012

Sg1 : Sg1 [%]	69
Sg2 : Sg2 [%]	6
Sg3 : Sg3 [%]	0

🔊 Acoustic properties

Direct airborne sound insulation - ESTIMATED : R_w (C;Ctr) [dB] ¹	39 (-1;-3)
--	------------

🛡️ Safety properties

Resistance to fire - EN 13501-2	NPD
Reaction to fire - EN 13501-1	A1
Bullet resistance - EN 1063	NPD
Burglar resistance - EN 356	P2A
Pendulum body impact resistance - EN 12600	1B1
Explosion resistance - EN 13541	NPD

Thickness and weight

Nominal thickness : [mm]	17.0
Weight : [kg/m ²]	43

¹ The sound reduction indexes are estimated and neither tested, nor calculated. They correspond to glazing with dimensions 1230 mm by 1480 mm according to EN ISO 10140-3. In-situ performances may vary according to the effective glazing dimensions, supporting system, installation, environment, noise sources etc. The accuracy of the given indexes is +/- 2 dB.